


Product Image



Product Dimensions



Characteristics

Nominal Voltage		12V
Nominal Capacity (10 hour rate)		300Ah
Capacity 25°C (77°F)	20 hour rate (16.6A)	333Ah
	5 hour rate (54.9A)	274.5Ah
	1 hour rate (219A)	219Ah
Internal Resistance	Full Charged Battery 25°C	≤2.0m Ω
Capacity affected by Temperature (10 hour)	40°C (104°F)	102%
	25°C (77°F)	100%
	0°C (32°F)	85%
	-15°C (5°F)	65%
Self-Discharge 25°C (77°F) Capacity	after 3 month storage	90%
	after 6 month storage	80%
	after 12 month storage	62%
Charge (Constant Voltage) 25°C (77°F)	Float	Initial Charging Current Less than 75A Voltage 13.6-13.8V
	Cycle	Initial Charging Current Less than 75A Voltage 14.4-14.9V

Packaging

Battery Dimensions	Length	521mm
	Width	269mm
	Height	220mm
	Total Height	224mm
Box Dimensions	Length	537mm
	Width	284mm
	Height	299mm
Quantity Per Box		1 PC per box
Net weight Per Cell		90 kg±500g
Net weight Per Box		90kg
Gross Weight		90.5kg

Discharge Constant Current per Cell (Amperes at 77°F25°C)







F.V/Time	5min	10min	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h
1.60V	840.6	560.0	422.0	262.7	188.4	166.3	101.4	74.1	47.7	29.1	26.0	14.4
1.65V	775.0	516.3	404.5	255.6	183.4	161.9	99.5	72.8	47.0	28.9	25.8	14.3
1.70V	788.1	525.0	386.9	248.6	178.3	157.3	97.7	71.4	46.4	28.6	25.5	14.2
1.75V	696.1	463.8	369.4	241.6	173.3	153.0	95.3	69.7	45.6	28.3	25.3	14.0
1.80V	656.7	437.5	351.7	234.5	168.3	148.4	93.0	68.0	45.0	28.0	25.0	13.9

Discharge Constant Power per Cell (Watts at 77°F 25°C)

F.V/Time	5min	10min	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h
1.60V	1567.8	1044.4	787.2	489.8	351.4	310.2	189.1	138.3	88.9	54.4	48.4	26.9
1.65V	1445.3	962.8	754.4	476.7	342.0	301.9	185.6	135.6	87.7	53.8	48.0	26.7
1.70V	1469.8	979.1	721.6	463.6	332.7	293.6	182.2	133.1	86.4	53.3	47.5	26.4
1.75V	1298.3	864.8	688.8	450.5	323.1	285.3	177.8	130.0	85.2	52.8	47.0	26.1
1.80V	1224.8	815.9	655.9	437.3	313.8	276.9	173.4	126.9	83.9	52.2	46.6	25.9

Note The above data are average values, and can be obtained within 3 charge/discharge cycles. These are not minimum values. Cell and battery designs/specifications are subject to modification without notice. Contact **US** for the latest information.

Performance Characteristics



Battery Construction

Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Si-Rubber	Lead	Fiberglass	Sulfuric acid

Guangdong JiYi General Electric Co., Ltd.

Overseas sales office Tel: +86-020-84869873 Fax: +86-020-34628335

Domestic sales office Tel: 020-34628335 Fax: 020-34628335

E-mail: ge@gerch.cn